

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
1 May 2003 (01.05.2003)

PCT

(10) International Publication Number
WO 03/035716 A1

(51) International Patent Classification⁷: **C08G 63/685**,
C30B 33/00, A61K 9/50, B01J 13/02, 13/22, C08B 37/00,
C08G 75/02, 75/20, C08J 5/22, C08G 59/42, 77/00, C09D
5/44, 167/06, H01B 13/06, 13/16, C08F 283/01, C08G
63/695, C08F 2/46, H01B 13/00

Newton, MA 02459 (US). **HAMMOND, Paula** [US/US];
235 Hartman Road, Newton, MA 02459 (US).

(74) Agent: **ROSEN, Valarie, B.**; Choate, Hall & Stewart, 53
State Street, Exchange Place, Boston, MA 02109 (US).

(21) International Application Number: PCT/US02/34191

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 25 October 2002 (25.10.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/335,213 25 October 2001 (25.10.2001) US

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK,
TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **MASSACHUSETTS INSTITUTE OF TECHNOLOGY**
[US/US]; 77 Massachusetts Avenue, Cambridge, MA
02139 (US).

(72) Inventors; and


(75) Inventors/Applicants (*for US only*): **LYNN, David, M.**
[US/US]; 3334 Conservancy Lane, Middleton, WI 53562
(US). **VAZQUEZ, Eduardo** [—/—]; Urb. Rexville, 61
Street AS-2, Bayamon, Puerto Rico, 00957-4224 (PR).
LANGER, Robert, S. [US/US]; 98 Montrale Road,

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHODS OF MAKING DECOMPOSABLE THIN FILMS OF POLYELECTROLYTES AND USES THEREOF



(57) Abstract: A decomposable thin film comprising a plurality of polyelectrolyte layers of alternating charge, wherein decomposition of the thin film is characterized by degradation of at least a portion of the polyelectrolyte layers.

WO 03/035716 A1

METHODS OF MAKING DECOMPOSABLE THIN FILMS OF POLYELECTROLYTES AND USES THEREOF

Government Funding

5 The work described herein was supported, in part, by grants from the National Institutes of Health (GM26698; NRSA Fellowship # 1 F32 GM20227-01). Accordingly, the Government may have certain rights in this invention.

Background of the Invention

10 The layer-by-layer (LBL) adsorption of oppositely-charged polyelectrolytes on surfaces has emerged as a simple, versatile, and inexpensive technique for the fabrication of thin multi-layer films, often with nanometer-scale control over the spatial distribution of ionized species within a film (Decher, G., *Science*, 277:1232-1237, 1997; Hammond P.T., *Curr. Opin. Coll. Interface Sci.*, 3:32-39, 1998).. First
15 introduced by Decher in the early 90's (see Decher and Hong, *Ber. Bunsenges. Phys. Chem.* 95:1430, 1991 and Decher, *Science*, 277:1232, 1997), the LBL approach is based on electrostatic attractions between polyelectrolytes and oppositely charged surfaces. In the example shown in Figure 1, a negatively charged substrate is first
20 dipped in a polycation solution. Electrostatic attractions result in deposition of the polycation and a resulting reversal of surface charge (see Figure 1, step 1). The positively charged substrate is then submerged in a polyanion solution, resulting in deposition of the polyanion and restoration of the negative charge on the surface (see Figure 1, step 2). Repetition of these steps leads to the buildup of layers of alternating
25 oppositely charged polyelectrolytes on the substrate surface. In addition to electrostatics, other factors and secondary interactions such as hydrophobicity, salt interactions, solvent quality, polymer concentrations, and deposition time may affect the multi-layer growth of the film (for a review of these factors, see Dubas and Schlenoff, *Macromolecules* 32:8153, 1999, the contents of which are incorporated herein by reference).

The array of materials available for LBL assembly is broad, including synthetic polyelectrolytes, conducting polymers, dyes, and metal colloids, as well as a variety of biological species such as proteins, viruses, and DNA. Applications as diverse as conductive and light-emitting films, biologically-active surfaces, selective
5 membranes, patterned films, and hollow multi-layer structures underscore the potential of the LBL technique (for a review of applications, see Hammond, *Curr. Opin. Coll. Interface Sci.* 3:32, 1998, the contents of which are incorporated herein by reference).

Despite the incorporation of new functionality, there are relatively few
10 examples of multi-layer thin films designed to *release* incorporated or encapsulated compounds. In particular, there remains a need in the art for thin film controlled release systems that function under physiological conditions.

Summary of the Invention

15 In one aspect, the invention is a decomposable thin film. The thin film comprises a plurality of polyelectrolyte layers of alternating charge. For example the thin film may comprise alternating polycationic and polyanionic layers. In certain embodiments, decomposition of the thin film is characterized by hydrolytic degradation of at least a portion of the polyelectrolyte layers. Additionally or
20 alternatively, decomposition of the thin film may be characterized by enzymatic, thermal, and/or photolytic degradation of at least a portion of the polyelectrolyte layers. The degradation rate need not be constant. The degradable polyelectrolytes may be synthetic, natural, or a mixture of both. The polyelectrolyte layers may, for example, include hydrolytically degradable polymers such as polyesters,
25 polyanhydrides, polyorthoesters, polyphosphazenes, polyphosphoesters, or any combination thereof. An anionic and/or cationic group may be incorporated into the polymer backbone, covalently attached to the polymer backbone, or attached to a pendant group of the polymer. The degradable polyelectrolytes may be zwitterionic polymers. The polyelectrolyte layers may further include biodegradable
30 polyelectrolytes. Additionally, the polyelectrolyte layers may include a mixture of

degradable and non-degradable polyelectrolytes. The degradation rate of the polyelectrolyte layers may be varied such that the decomposition rate of the thin film is not a constant. A layer of cells may be deposited on the surface of the thin film. The thin films may include electroactive polymers. A portion of the layers may
5 comprise a biomolecule, small molecule, bioactive agent, or some combination of these. The concentration of the biomolecule, small molecule, or bioactive agent may vary with depth, and it may be associated with or mixed with the polyelectrolytes in a layer of the thin film. A cell adhesion sequence, targeting sequence, or both may be
10 disposed in the top layer of the thin film. The film may be deposited upon a non-planar substrate or may be a hollow shell. The substrate may diffuse through the thin film or dissolve after decomposition of the thin film.

In another aspect, the invention is a method of releasing an entity from a thin film. The method comprises associating or mixing the entity with a thin film comprising a plurality of polyelectrolyte layers of alternating charge and placing the
15 thin film in a medium in which at least a portion of the thin film decomposes via the substantially sequential degradation of at least a portion of the polyelectrolyte layers. The degradation may be at least partially hydrolytic, at least partially enzymatic, at least partially thermal, and/or at least partially photolytic. The substrate material may be allowed to diffuse through the thin film or may be dissolved following
20 decomposition of the thin film. The method may further comprise placing the thin film in a second medium in which a second portion of the thin film decomposes. The medium may be characterized by endosomal conditions or physiological conditions. The method may include adding a primer layer interposed between the thin film and the substrate. The method may further comprise producing the thin film via layer-by-
25 layer assembly. For example, the polyelectrolyte layers may be deposited by dip coating, spray coating, brush coating, roll coating, spin casting, or some combination of these. After predetermined layers are deposited, the entity may be associated with them.

In another aspect, the invention is a method of generating a three dimensional
30 microstructure on a substrate surface. The method comprises creating a charged

region on a substrate surface, depositing a plurality of polyelectrolyte layers of alternating charge on the charged region, depositing a first non-degradable material over the substrate and the plurality of polyelectrolyte layers, and placing the coated substrate in a medium in which at least a portion of the polyelectrolyte layers degrade.

5 The surface composition of the substrate may vary. The charged region may be created by stamping a self-assembled monolayer, by depositing a uniform coating of a polymer on the substrate surface and patterning the uniform coating by photolithography, or by selectively exposing the substrate surface to plasmas, electromagnetic radiation, or electron beams. Following a step of depositing the first

10 non-degradable material, the method may further comprise creating a charged region on the first non-degradable material, depositing a plurality of polyelectrolyte layers of alternating charge on the charged region, and depositing a second non-degradable material over the first non-degradable material and the plurality of layers. Of course, the two non-degradable materials may be the same or different and the methods used

15 to create the charged region or regions may be the same or different.

Definitions

“**Animal**”: The term animal, as used herein, refers to humans as well as non-human animals, including, for example, mammals, birds, reptiles, amphibians, and

20 fish. Preferably, the non-human animal is a mammal (*e.g.*, a rodent, a mouse, a rat, a rabbit, a monkey, a dog, a cat, a primate, or a pig). An animal may be a transgenic animal.

“**Associated with**”: When two entities are “associated with” one another as described herein, they are linked by a direct or indirect covalent or non-covalent

25 interaction. Desirable non-covalent interactions include hydrogen bonding, van der Waals interactions, hydrophobic interactions, magnetic interactions, electrostatic interactions, *etc.* Preferred non-covalent interactions are electrostatic interactions and hydrogen bonds.

“**Biomolecules**”: The term “biomolecules”, as used herein, refers to

30 molecules (*e.g.*, proteins, amino acids, peptides, polynucleotides, nucleotides,

carbohydrates, sugars, lipids, nucleoproteins, glycoproteins, lipoproteins, steroids, etc.) whether naturally-occurring or artificially created (*e.g.*, by synthetic or recombinant methods) that are commonly found in cells and tissues. Specific classes of biomolecules include, but are not limited to, enzymes, receptors, neurotransmitters, hormones, cytokines, cell response modifiers such as growth factors and chemotactic factors, antibodies, vaccines, haptens, toxins, interferons, ribozymes, anti-sense agents, plasmids, DNA, and RNA.

“Biocompatible”: The term “biocompatible”, as used herein is intended to describe materials that do not elicit a substantial detrimental response *in vivo*.

10 **“Biodegradable”**: As used herein, “biodegradable” polymers are polymers that degrade fully under physiological or endosomal conditions. In preferred embodiments, the polymers and biodegradation byproducts are biocompatible. Biodegradable polymers are not necessarily hydrolytically degradable and may require enzymatic action to fully degrade.

15 **“Degradation”**: The phrase “degradation”, as used herein, relates to the cleavage of a covalent polymer backbone. Full degradation of a polymer breaks the polymer down to monomeric species.

“Endosomal conditions”: The phrase “endosomal conditions”, as used herein, relates to the range of chemical (*e.g.*, pH, ionic strength) and biochemical (20 *e.g.*, enzyme concentrations) conditions likely to be encountered within endosomal vesicles. For most endosomal vesicles, the endosomal pH ranges from about 5.0 to 6.5.

“Hydrolytically degradable”: As used herein, “hydrolytically degradable” polymers are polymers that degrade fully in the sole presence of water. In preferred 25 embodiments, the polymers and hydrolytic degradation byproducts are biocompatible. As used herein, the term “non-hydrolytically degradable” refers to polymers that do not fully degrade in the sole presence of water.

“Physiological conditions”: The phrase “physiological conditions”, as used herein, relates to the range of chemical (*e.g.*, pH, ionic strength) and biochemical 30 (*e.g.*, enzyme concentrations) conditions likely to be encountered in the intracellular

and extracellular fluids of tissues. For most tissues, the physiological pH ranges from about 7.0 to 7.4.

“Polyelectrolyte” or “polyion”: The terms “polyelectrolyte” or “polyion”, as used herein, refer to a polymer which under some set of conditions (*e.g.*, physiological conditions) has a net positive or negative charge. Polycations have a net positive charge and polyanions have a net negative charge. The net charge of a given polyelectrolyte or polyion may depend on the surrounding chemical conditions, *e.g.*, on the pH.

“Polynucleotide”, “nucleic acid”, or “oligonucleotide”: The terms “polynucleotide”, “nucleic acid”, or “oligonucleotide” refer to a polymer of nucleotides. The terms “polynucleotide”, “nucleic acid”, and “oligonucleotide”, may be used interchangeably. Typically, a polynucleotide comprises at least three nucleotides. DNAs and RNAs are polynucleotides. The polymer may include natural nucleosides (*i.e.*, adenosine, thymidine, guanosine, cytidine, uridine, deoxyadenosine, deoxythymidine, deoxyguanosine, and deoxycytidine), nucleoside analogs (*e.g.*, 2-aminoadenosine, 2-thiothymidine, inosine, pyrrolo-pyrimidine, 3-methyl adenosine, C5-propynylcytidine, C5-propynyluridine, C5-bromouridine, C5-fluorouridine, C5-iodouridine, C5-methylcytidine, 7-deazaadenosine, 7-deazaguanosine, 8-oxoadenosine, 8-oxoguanosine, O(6)-methylguanine, and 2-thiocytidine), chemically modified bases, biologically modified bases (*e.g.*, methylated bases), intercalated bases, modified sugars (*e.g.*, 2'-fluororibose, ribose, 2'-deoxyribose, arabinose, and hexose), or modified phosphate groups (*e.g.*, phosphorothioates and 5'-N-phosphoramidite linkages).

“Polypeptide”, “peptide”, or “protein”: According to the present invention, a “polypeptide”, “peptide”, or “protein” comprises a string of at least three amino acids linked together by peptide bonds. The terms “polypeptide”, “peptide”, and “protein”, may be used interchangeably. Peptide may refer to an individual peptide or a collection of peptides. Inventive peptides preferably contain only natural amino acids, although non-natural amino acids (*i.e.*, compounds that do not occur in nature but that can be incorporated into a polypeptide chain; see, for example,

<http://www.cco.caltech.edu/~dadgrp/Unnatstruct.gif>, which displays structures of non-natural amino acids that have been successfully incorporated into functional ion channels) and/or amino acid analogs as are known in the art may alternatively be employed. Also, one or more of the amino acids in an inventive peptide may be
5 modified, for example, by the addition of a chemical entity such as a carbohydrate group, a phosphate group, a farnesyl group, an isofarnesyl group, a fatty acid group, a linker for conjugation, functionalization, or other modification, *etc.* In a preferred embodiment, the modifications of the peptide lead to a more stable peptide (*e.g.*, greater half-life *in vivo*). These modifications may include cyclization of the peptide,
10 the incorporation of D-amino acids, *etc.* None of the modifications should substantially interfere with the desired biological activity of the peptide.

“Polysaccharide”, “carbohydrate” or “oligosaccharide”: The terms “polysaccharide”, “carbohydrate”, or “oligosaccharide” refer to a polymer of sugars. The terms “polysaccharide”, “carbohydrate”, and “oligosaccharide”, may be used
15 interchangeably. Typically, a polysaccharide comprises at least three sugars. The polymer may include natural sugars (*e.g.*, glucose, fructose, galactose, mannose, arabinose, ribose, and xylose) and/or modified sugars (*e.g.*, 2'-fluororibose, 2'-deoxyribose, and hexose).

“Small molecule”: As used herein, the term “small molecule” is used to refer
20 to molecules, whether naturally-occurring or artificially created (*e.g.*, via chemical synthesis), that have a relatively low molecular weight. Typically, small molecules are monomeric and have a molecular weight of less than about 1500 g/mol. Preferred small molecules are biologically active in that they produce a local or systemic effect in animals, preferably mammals, more preferably humans. In certain preferred
25 embodiments, the small molecule is a drug. Preferably, though not necessarily, the drug is one that has already been deemed safe and effective for use by the appropriate governmental agency or body. For example, drugs for human use listed by the FDA under 21 C.F.R. §§ 330.5, 331 through 361, and 440 through 460; drugs for veterinary use listed by the FDA under 21 C.F.R. §§ 500 through 589, incorporated herein by

reference, are all considered acceptable for use in accordance with the present invention.

“Bioactive agents”: As used herein, “bioactive agents” is used to refer to compounds or entities that alter, inhibit, activate, or otherwise affect biological or chemical events. For example, bioactive agents may include, but are not limited to, anti-AIDS substances, anti-cancer substances, antibiotics, immunosuppressants, anti-viral substances, enzyme inhibitors, neurotoxins, opioids, hypnotics, anti-histamines, lubricants, tranquilizers, anti-convulsants, muscle relaxants and anti-Parkinson substances, anti-spasmodics and muscle contractants including channel blockers, miotics and anti-cholinergics, anti-glaucoma compounds, anti-parasite and/or anti-protozoal compounds, modulators of cell-extracellular matrix interactions including cell growth inhibitors and anti-adhesion molecules, vasodilating agents, inhibitors of DNA, RNA or protein synthesis, anti-hypertensives, analgesics, anti-pyretics, steroidal and non-steroidal anti-inflammatory agents, anti-angiogenic factors, anti-secretory factors, anticoagulants and/or antithrombotic agents, local anesthetics, ophthalmics, prostaglandins, anti-depressants, anti-psychotic substances, anti-emetics, and imaging agents. In certain embodiments, the bioactive agent is a drug.

A more complete listing of bioactive agents and specific drugs suitable for use in the present invention may be found in “Pharmaceutical Substances: Syntheses, Patents, Applications” by Axel Kleemann and Jurgen Engel, Thieme Medical Publishing, 1999; the “Merck Index: An Encyclopedia of Chemicals, Drugs, and Biologicals”, Edited by Susan Budavari *et al.*, CRC Press, 1996, and the United States Pharmacopeia-25/National Formulary-20, published by the United States Pharmacopeial Convention, Inc., Rockville MD, 2001, all of which are incorporated herein by reference.

Acronyms

The following acronyms are used herein: “SPS” is poly(styrene sulfonate), “PAA” is poly(acrylic acid), “LPEI” is linear poly(ethylene imine), “PDAC” is

poly(diallyl dimethyl ammonium chloride), "PAH" is poly(allylamine hydrochloride), and "PAZO" is the azobenzene functionalized polymer poly{1-[4-(3-carboxy-4-hydroxyphenylazo) benzensulfonamido]-1,2 -ethanediyl}.

5

Description of the Drawing

The invention is described with reference to several figures of the drawing, in which:

Figure 1 is a schematic illustrating the construction of a thin film via layer-by-layer deposition of polyelectrolytes on a charged substrate;

10

Figure 2 is a schematic illustrating the construction and decomposition of a thin film according to one embodiment of the invention by (A) layer-by-layer deposition of alternating polyanionic and polycationic layers and (B) degradation of polycationic layers and release of polyanionic components;

15

Figure 3 depicts the chemical structure of exemplary hydrolytically degradable polycations for the fabrication of a decomposable thin film;

Figure 4 depicts the chemical structure of exemplary non-degradable polyanions and polycations for the fabrication of a thin film according to one embodiment of this invention;

20

Figure 5 is a schematic illustrating entities (shown as black triangles), *e.g.*, biomolecules or small molecules that are non-covalently associated with polycations of a thin film according to one embodiment of the invention;

Figure 6 is a schematic illustrating entities (shown as black triangles), *e.g.*, biomolecules or small molecules that are covalently associated with polycations of a thin film according to one embodiment of the invention;

25

Figure 7 depicts the chemical structure of PAZO, an azobenzene functionalized photochromic polyanion;

Figure 8 is a schematic illustrating the deposition of a decomposable thin film on a particulate template and construction of a decomposable hollow thin film microcapsule by dissolution of the template;

Figure 9 is a schematic illustrating the construction of a tunnel-like microstructure according to one embodiment of the invention by (A) deposition of an ionic or polar self-assembled monolayer (SAM), *e.g.*, by micro-contact printing, (B) layer-by-layer deposition of a decomposable thin film, (C) flooding of the substrate with a non-degradable material, and (D) decomposition of the thin film;

Figure 10 depicts the chemical structure of Polymer 1 (Poly 1), a hydrolytically degradable poly(β -amino ester);

Figure 11 is a profilometry scan of ten bilayers of Poly 1/SPS deposited on ten precursor bilayers of LPEI/SPS;

Figure 12 illustrates the thickness change as bilayers of Poly 1/SPS are deposited on ten precursor bilayers of LPEI/SPS;

Figure 13 is a reflective FTIR scan of ten bilayers of Poly 1/SPS deposited on ten precursor bilayers of LPEI/SPS on a gold substrate (1734 cm^{-1} carboxyl stretch indicated);

Figure 14 illustrates the decomposition in PBS buffer at pH 7.4 (at 37°C) of a thin film comprising Poly 1/SPS bilayers deposited on precursor bilayers of LPEI/SPS;

Figure 15 illustrates the decomposition in TAE buffer at pH 8.3 (at 37°C) of a thin film comprising Poly 1/SPS bilayers deposited on precursor bilayers of LPEI/SPS;

Figure 16 illustrates the thickness of six different thin films comprising Poly 1/DNA bilayers deposited on ten precursor bilayers of LPEI/SPS; and

Figure 17 illustrates the decomposition in PBS buffer at pH 7.4 (at 37°C) of a thin film comprising Poly 1/DNA bilayers deposited on precursor bilayers of LPEI/SPS.

Detailed Description

The present invention provides a method for the gradual and controlled release of one or more entities from decomposable thin films. The decomposition is

characterized by the substantially sequential degradation of at least a portion of the polyelectrolyte layers that make up the thin films. The degradation may be at least partially hydrolytic, at least partially enzymatic, at least partially thermal, and/or at least partially photolytic.

5 Several groups have reported the deposition of polyelectrolytes onto microcrystalline templates to yield semi-permeable films that release compounds via diffusion (see Qiu *et al.*, *Langmuir* 17:5375, 2001 and Antipov *et al.*, *J. Phys. Chem. B* 105:2281, 2001). However, while multi-layer films are permeable to small molecules (*e.g.*, ibuprofen and fluorescein), they are much less permeable to
10 molecules with molecular weights larger than 4 kDa (see Sukhorukov *et al.*, *J. Phys. Chem. B* 103:6434, 1999), and are therefore less well-suited to the diffusive release of biomolecules, *e.g.*, DNA, RNA, and proteins.

Recent work has also demonstrated that certain multi-layer films can be “deconstructed” at high salt concentrations (see Dubas and Schlenoff,
15 *Macromolecules* 34:3736, 2001). As described by Dubas and Schlenoff, at high salt concentrations the free ions compete for the charged groups of the polyelectrolytes and hence weaken intermolecular interactions within the film, thereby causing it to fall apart. This concept has been extended to the fabrication of films that release DNA in the presence of salt (see Schüler and Caruso, *Biomacromolecules* 2:921,
20 2001). Unfortunately, deconstruction occurs under conditions of high ionic strength (*e.g.*, salt concentrations of 0.6 - 5 M), and is therefore not well-suited to the release of molecules under physiological conditions.

In certain embodiments of the instant invention, the released entities are structural polyelectrolyte components of the inventive films. One such embodiment
25 of the invention is illustrated in Figure 2. In step A of this embodiment, the thin film is deposited on a substrate via layer-by-layer assembly as depicted in Figure 1. The thin film includes a plurality of alternating polyanionic and polycationic layers. The polycationic layers include a degradable polycation. In step B, the thin film is exposed to a degrading medium (*e.g.*, intracellular fluid), whereupon the polycationic
30 layers degrade and the polyanionic layers delaminate sequentially from the surface

toward the substrate. The component polyanions of the exposed polyanionic layers are thus gradually and controllably released from the surface of the thin film. In preferred embodiments, the released polyanions are biomolecules, for example, DNA molecules. If the thin film is to be disposed *in vivo*, the polycations and their
5 degradation byproducts are preferably biocompatible. It will be appreciated that the roles of the two layers of the thin film can be reversed. In such embodiments, the polyanionic layers include a degradable polyanion and the polycationic layers may include, for example, a polycationic protein. Alternatively, both the polycationic and polyanionic layers may both include degradable polyelectrolytes.

10 A variety of materials can be used as substrates of the present invention such as, but not limited to, metals, *e.g.*, gold, silver, platinum, and aluminum; metal-coated materials; metal oxides; plastics; ceramics; silicon; glasses; mica; graphite; hydrogels; polymers such as polyamides, polyphosphazenes, polypropylfumarates, polyethers, polyacetals, polycyanoacrylates, polyurethanes, polycarbonates, polyanhydrides,
15 polyorthoesters, polyhydroxyacids, polyacrylates, ethylene vinyl acetate polymers and other cellulose acetates, polystyrenes, poly(vinyl chloride), poly(vinyl fluoride), poly(vinyl imidazole), poly(vinyl alcohol), poly(ethylene terephthalate), polyesters, polyureas, polypropylene, polymethacrylate, polyethylene, poly(ethylene oxide)s and chlorosulphonated polyolefins; and combinations thereof. For example, a substrate of
20 one material may be coated with a second material, or two materials may be combined to form a composite.

It will be appreciated that materials with an inherently charged surface are particularly attractive substrates for LBL assembly of an inventive thin film. Alternatively, a range of methods are known in the art that can be used to charge the
25 surface of a material, including but not limited to plasma processing, corona processing, flame processing, and chemical processing, *e.g.*, etching, micro-contact printing, and chemical modification. For example, plastics can be used as substrates, particularly if they have been chemically modified to present polar or charged functional groups on the surface. Additionally or alternatively, substrates can be
30 primed with specific polyelectrolyte bilayers such as, but not limited to, LPEI/SPS,

PDAC/SPS, PAH/SPS, LPEI/PAA, PDAC/PAA, and PAH/PAA bilayers, that form readily on weakly charged surfaces and occasionally on neutral surfaces. It will be appreciated that primer layers provide a uniform surface layer for further LBL assembly and are therefore particularly well suited to applications that require the deposition of a uniform thin film on a substrate that includes a range of materials on its surface, *e.g.*, an implant or a complex tissue engineering construct.

Any degradable polyelectrolyte can be used in a thin film of the present invention, including, but not limited to, hydrolytically degradable, biodegradable, thermally degradable, and photolytically degradable polyelectrolytes. Hydrolytically degradable polymers known in the art include for example, certain polyesters, polyanhydrides, polyorthoesters, polyphosphazenes, and polyphosphoesters. Biodegradable polymers known in the art, include, for example, certain polyhydroxyacids, polypropylfumerates, polycaprolactones, polyamides, poly(amino acids), polyacetals, polyethers, biodegradable polycyanoacrylates, biodegradable polyurethanes and polysaccharides. For example, specific biodegradable polymers that may be used in the present invention include but are not limited to polylysine, poly(lactic acid) (PLA), poly(glycolic acid) (PGA), poly(caprolactone) (PCL), poly(lactide-co-glycolide) (PLG), poly(lactide-co-caprolactone) (PLC), and poly(glycolide-co-caprolactone) (PGC). Those skilled in the art will recognize that this is an exemplary, not comprehensive, list of biodegradable polymers. The properties of these and other polymers and methods for preparing them are further described in the art. See, for example, U.S. Patents Nos. 6,123,727; 5,804,178; 5,770,417; 5,736,372; 5,716,404 to Vacanti; 6,095,148; 5,837,752 to Shastri; 5,902,599 to Anseth; 5,696,175; 5,514,378; 5,512,600 to Mikos; 5,399,665 to Barrera; 5,019,379 to Domb; 5,010,167 to Ron; 4,806,621; 4,638,045 to Kohn; and 4,946,929 to d'Amore; see also Wang *et al.*, *J. Am. Chem. Soc.* 123:9480, 2001; Lim *et al.*, *J. Am. Chem. Soc.* 123:2460, 2001; Langer, *Acc. Chem. Res.* 33:94, 2000; Langer, *J. Control Release* 62:7, 1999; and Uhrich *et al.*, *Chem. Rev.* 99:3181, 1999. Of course, co-polymers, mixtures, and adducts of these polymers may also be employed.

The anionic polyelectrolytes are preferably degradable polymers with anionic groups distributed along the polymer backbone. The anionic groups, which may include carboxylate, sulfonate, sulphate, phosphate, nitrate, or other negatively charged ionizable groupings, may be disposed upon groups pendant from the backbone or may be incorporated in the backbone itself. The cationic polyelectrolytes are preferably degradable polymers with cationic groups distributed along the polymer backbone. The cationic groups, which may include protonated amine, quaternary ammonium or phosphonium derived functions, may be disposed in side groups pendant from the backbone, may be attached to the backbone directly, or can be incorporated in the backbone itself.

For example, a range of hydrolytically degradable amine containing polyesters bearing cationic side chains have recently been developed (Putnam *et al.* *Macromolecules* 32:3658-3662, 1999; Barrera *et al.* *J. Am. Chem. Soc.* 115:11010-11011, 1993; Kwon *et al.* *Macromolecules* 22:3250-3255, 1989; Lim *et al.* *J. Am. Chem. Soc.* 121:5633-5639, 1999; Zhou *et al.* *Macromolecules* 23:3399-3406, 1990; each of which is incorporated herein by reference). Examples of these polyesters include poly(L-lactide-co-L-lysine) (Barrera *et al.* *J. Am. Chem. Soc.* 115:11010-11011, 1993; incorporated herein by reference), poly(serine ester) (Zhou *et al.* *Macromolecules* 23:3399-3406, 1990; which is incorporated herein by reference), poly(4-hydroxy-L-proline ester) (Putnam *et al.* *Macromolecules* 32:3658-3662, 1999.; Lim *et al.* *J. Am. Chem. Soc.* 121:5633-5639, 1999; each of which is incorporated herein by reference), and more recently, poly[α -(4-aminobutyl)-L-glycolic acid].

In addition, poly(β -amino ester)s, prepared from the conjugate addition of primary or secondary amines to diacrylates, are suitable for use with the invention. Typically, poly(β -amino ester)s have one or more tertiary amines in the backbone of the polymer, preferably one or two per repeating backbone unit. Alternatively, a copolymer may be used in which one of the components is a poly(β -amino ester). Poly(β -amino ester)s are described in USSN 09/969,431, filed October 2, 2001, entitled "Biodegradable poly(β -amino esters) and uses thereof" and Lynn *et al.*, *J.*

Am. Chem. Soc. 122:10761-10768, 2000, the entire contents of both of which are incorporated herein by reference.

Exemplary poly(β -amino ester)s are shown in Figure 3. Exemplary R groups include hydrogen, branched and unbranched alkyl, branched and unbranched alkenyl, branched and unbranched alkynyl, aryl, halogen, hydroxyl, alkoxy, carbamoyl, carboxyl ester, carbonyldioxyl, amide, thiohydroxyl, alkylthioether, amino, alkylamino, dialkylamino, trialkylamino, cyano, ureido, a substituted alkanoyl group, cyclic, cyclic aromatic, heterocyclic, and aromatic heterocyclic groups, each of which may be substituted with at least one substituent selected from the group consisting of branched and unbranched alkyl, branched and unbranched alkenyl, branched and unbranched alkynyl, amino, alkylamino, dialkylamino, trialkylamino, aryl, ureido, heterocyclic, aromatic heterocyclic, cyclic, aromatic cyclic, halogen, hydroxyl, alkoxy, cyano, amide, carbamoyl, carboxylic acid, ester, carbonyl, carbonyldioxyl, alkylthioether, and thiol groups.

Exemplary linker groups A and B include carbon chains of 1 to 30 carbon atoms, heteroatom-containing carbon chains of 1 to 30 atoms, and carbon chains and heteroatom-containing carbon chains with at least one substituent selected from the group consisting of branched and unbranched alkyl, branched and unbranched alkenyl, branched and unbranched alkynyl, amino, alkylamino, dialkylamino, trialkylamino, aryl, ureido, heterocyclic, aromatic heterocyclic, cyclic, aromatic cyclic, halogen, hydroxyl, alkoxy, cyano, amide, carbamoyl, carboxylic acid, ester, carbonyl, carbonyldioxyl, alkylthioether, and thiol groups. The polymer preferably has between 5 and 10,000 repeat units.

Alternatively, zwitterionic polyelectrolytes may be used. Such polyelectrolytes may have both anionic and cationic groups incorporated into the backbone or covalently attached to the backbone as part of a pendant group. Such polymers may be neutrally charged at one pH, positively charged at another pH, and negatively charged at a third pH. For example, a film may be deposited by LBL deposition using dip coating in solutions of a first pH at which one layer is anionic and a second layer is cationic. If the film is put into a solution having a second

different pH, then the first layer may be rendered cationic while the second layer is rendered anionic, thereby changing the charges on those layers.

In certain embodiments, the LBL assembly of inventive films may involve a series of dip coating steps in which the substrate is dipped in alternating polycationic and polyanionic solutions (see Figure 1). Additionally or alternatively, it will be appreciated that deposition of alternating polycationic and polyanionic layers may also be achieved by spray coating, brush coating, roll coating, spin casting, or combinations thereof.

The composition of the polyanionic and polycationic layers can be fine-tuned to adjust the degradation rate of each layer within the film. For example, the degradation rate of hydrolytically degradable polyelectrolyte layers can be decreased by associating hydrophobic polymers such as hydrocarbons and lipids with one or more of the layers. Alternatively, the polyelectrolyte layers may be rendered more hydrophilic to increase their hydrolytic degradation rate. In certain embodiments, the degradation rate of a given layer can be adjusted by including a mixture of polyelectrolytes that degrade at different rates or under different conditions. In other embodiments, the polyanionic and/or polycationic layers may include a mixture of degradable and non-degradable polyelectrolytes. Any non-degradable polyelectrolyte can be used with the present invention. Exemplary non-degradable polyelectrolytes that could be used in thin films of the present invention are shown in Figure 4 and include poly(styrene sulfonate) (SPS), poly(acrylic acid) (PAA), linear poly(ethylene imine) (LPEI), poly(diallyldimethyl ammonium chloride) (PDAC), and poly(allylamine hydrochloride) (PAH).

Alternatively or additionally, the degradation rate may be fine-tuned by associating or mixing non-biodegradable, yet biocompatible polymers (polyionic or non-polyionic) with one or more of the polyanionic and/or polycationic layers. Suitable non-biodegradable, yet biocompatible polymers are well known in the art and include polystyrenes, certain polyesters, non-biodegradable polyurethanes, polyureas, poly(ethylene vinyl acetate), polypropylene, polymethacrylate, polyethylene, polycarbonates, and poly(ethylene oxide)s.

Furthermore, because the thin film is produced in a layer-by-layer fashion, the composition of individual layers may be varied to tailor the degradation rate of various portions of the film. For example, the upper layers of the film, closer to the surface, may be adjusted to degrade faster than the layers of the film closer to the substrate, or vice versa. Depending on the thickness of the film, the degradation rate within the film may be varied cyclically (*e.g.*, for periodic release). Additionally or alternatively, the upper layers of the film, closer to the surface, may be adjusted to degrade under a first set of conditions (*e.g.*, endosomal conditions) while the layers of the film that are closer to the substrate are adjusted to degrade under a second set of conditions (*e.g.*, physiological conditions).

The released entity need not act as a structural component of the film (see Figures 5 and 6). As noted above, polyelectrolytes may be associated or mixed with polymeric or non-polymeric moieties to regulate the degradation rate. In addition, neutral, zwitterionic, or charged biomolecules, small molecules, or bioactive agents may be associated or mixed with a polycation or polyanion and incorporated into a layer. For example, the charged atoms on a zwitterionic molecule may facilitate electrostatic interactions with both the polyanionic and polycationic layers. A zwitterionic biomolecule, small molecule, or bioactive agent may be combined in solution with the polyelectrolytes for one of the layers or placed in a separate solution to form a "sandwich" between two layers. When the thin film degrades, the biomolecule, small molecule, or bioactive agent will be released. Alternatively, a biomolecule, small molecule, or bioactive agent may be associated with a polyelectrolyte under conditions which facilitate a strong interaction between the molecule and the polyelectrolyte, while the medium in which the biomolecule, small molecule, or bioactive agent is released is one which competes with the polyelectrolyte for the biomolecule, small molecule, or bioactive agent, thereby decreasing the strength of the interaction with the polyelectrolyte.

The composition of the various layers may be adjusted to release different entities as the thin film degrades. For example, a thin film may be designed to release a chemotactic factor tailored to attract cells to an implant site for a specified number

of layers, followed by a growth factor tailored to stimulate a desired metabolic or proliferative activity in cells now at the implant site.

It will be appreciated that in preparing a thin film that degrades with a desired rate and profile one may need to test various thin film compositions experimentally.

- 5 The degradation rates and profiles of inventive thin films can, for example, be investigated using a variety of known techniques, including ellipsometry, dynamic light scattering (DLS), zeta-potential analysis, quartz crystal microbalance (QCM), and atomic force microscopy (AFM). The QCM method is particularly attractive since it can be used with rough films and allows continuous monitoring without
10 removal of the thin films from the degradation milieu. AFM can be also used to monitor changes in the multi-layer surface morphology as a function of degradation.

- Additionally or alternatively, one may choose to monitor the rate at which a non-degradable structural polymer, biomolecule, small molecule, or bioactive agent is released from the thin film. If the released entity absorbs or emits light in an
15 uncrowded region of the ultraviolet or visible electromagnetic spectrum, one could measure the rate of release by UV-visible spectroscopy. It will be appreciated that a variety of synthetic and recombinant techniques exist that allow one to attach a light absorbing or emitting group, *e.g.*, a fluorescent group or a dye to a polymer or small molecule that lacks such functionality. Alternatively, one could incorporate a model
20 chromic compound, *e.g.*, the commercially available photochromic polyanion PAZO (see Figure 7), into a range of thin films for this purpose.

- The thin film may also be used to create a degradable substrate for cell seeding and culture. Some cells, for example, chondrocytes, proliferate better when deposited on a substrate to which they can attach. However, to use these cells in other
25 applications, they may need to be separated from the substrate. Cells may be deposited on the surface of a multi-layer thin film and maintained *in vitro*. As the thin film degrades, the cells are released into the surrounding medium, freeing them for seeding onto tissue engineering matrices or for analysis. Integrins and cell adhesion sequences (*e.g.*, the RGD sequence) may be included in the top layer or layers of the
30 film to facilitate cell adhesion. Integrins are part of a large family of cell adhesion

receptors which are involved in cell-extracellular matrix and cell-cell interactions. The RGD sequence, present in proteins such as fibronectin, has been shown to be active in promoting cell adhesion and proliferation (see Massia *et al.*, *J. Cell. Biol.* 114:1089, 1991).

5 The thin films may include electroactive polymers. In the presence or absence of a voltage, conductive polymers may enhance the proliferation and metabolism of cells deposited thereon (USPN 6,095,148, issued Aug. 1, 2000, and 6,190,893, issued Feb. 20, 2001). The voltage may be an externally applied voltage. Alternatively, a voltage may be applied by native tissue, for example, nerve. Bone is piezoelectric,
10 and physiologic loading will generate a potential across a film implanted therein. Exemplary electroactive polymers include, but are not limited to, polypyrrole, poly(p-phenylene), poly(p-phenylene vinylene), polythiophene, polyaniline, polyporphyrin, polyheme, and derivatives thereof. These polymers may be derivatized. For example,
15 hydrocarbon groups, methoxy, cyano, phenyl, alkoxy, amino, and halides may be added to aromatic groups in the polymer, and except for halides (which would lead to the production of poly(phenylene acetylene)), to the non-aromatic carbons. Of course, if the film is intended for biological applications, the resulting derivative should be biocompatible.

 The invention can employ a wide range of cell types and is not limited to any
20 specific cell type. Examples of cell types that may be used include but are not limited to bone or cartilage forming cells such as chondrocytes and fibroblasts, other connective tissue cells, epithelial cells, endothelial cells, blood vessel cells, cancer cells, organ cells such as hepatocytes, islet cells, kidney cells, intestinal cells, and lymphocytes, smooth muscle cells, skeletal muscle cells, heart muscle cells, nerve
25 cells, and stem cells such as human embryonic stem cells or mesenchymal stem cells.

 In another embodiment, the thin film may encapsulate a decomposable substrate (*e.g.*, a drug nano- or micro-crystal). Additionally or alternatively, the thin film may be exploited to regulate diffusion of the substrate into the surrounding medium. In certain embodiments, particularly for drug delivery, it may be desirable
30 to target an encapsulated substrate to a particular cell or tissue. A variety of agents

that can direct an encapsulated substrate to particular cells are known in the art (see, for example, Cotten *et al.*, *Methods Enzym.* 217:618, 1993). Examples of useful targeting agents include, but are in no way limited to, low-density lipoproteins (LDLs), transferrin, asialoglycoproteins, gp120 envelope protein of the human immunodeficiency virus (HIV), toxins, antibodies, and carbohydrates. Certain preferred encapsulated substrates of the present invention include one or more targeting agents that are associated with polyelectrolyte components of the inventive thin film and/or with the entity to be released.

The substrate geometry may be manipulated to deposit films having a variety of shapes. For example, films may be deposited on particles, tubes, or spheres to facilitate a more uniform release distribution. Films may be deposited on strands such as sutures to release factors such as analgesics or antibiotics at a surgical site. Alternatively, these films may be deposited onto capillary networks or tissue engineering constructs. For example, a thin film deposited on a three-dimensional tissue engineering construct may be used to attract cells to a newly implanted construct and then to promote specific metabolic or proliferative activity.

The methods of the invention may also be used to create three-dimensional microstructures. For example, the thin film may be deposited on a substrate that can be dissolved to leave a hollow shell of the thin film (see Figure 8). Alternatively, multi-layers may be deposited having regions that are more and less degradable. Degradation of the degradable portions leaves a three-dimensional microstructure (see Figure 9). In a first step, the surface of a substrate is divided into regions in which LBL deposition of an inventive thin film is more or less favorable (see Figure 9, step A). In one embodiment, a pattern of self-assembled monolayers (SAMs) is deposited on a substrate surface by microcontact printing (see, for example, U.S. Patent No. 5,512,131 to Kumar *et al.*, see also Kumar *et al.*, *Langmuir* 10:1498, 1994; Jiang and Hammond, *Langmuir*, 16:8501, 2000; Clark *et al.*, *Supramolecular Science* 4:141, 1997; and Hammond and Whitesides, *Macromolecules* 28:7569, 1995). In preferred embodiments, the substrate surface is neutral and the exposed surface of the deposited SAMs is polar or ionic (*i.e.*, charged). A variety of polymers with polar or ionic head

groups are known in the art of self-assembled monolayers. In another embodiment, a uniform coating of a polymer is deposited on a substrate, and that coating is transformed into a patterned layer by means of photolithography. Other embodiments are also contemplated in which the substrate surface is selectively exposed to plasmas, various forms of electromagnetic radiation, or to electron beams. In yet other
5 embodiments, the substrate may possess the desired surface characteristics by virtue of its inherent composition. For example, the substrate may be a composite in which different regions of the surface have differing compositions, and thus different affinities for the polyelectrolyte to be deposited.

10 In a second step, polyelectrolyte layers of alternating charge are deposited by LBL on receptive regions of the surface (see Figure 9, step B) as described for a homogeneous surface above and selective regions in Jiang and Hammond, *Langmuir*, 16:8501, 2000; Clark *et al.*, *Supramolecular Science* 4:141, 1997; and Hammond and Whitesides, *Macromolecules* 28:7569, 1995. The surface is subsequently flooded
15 with a non-degradable polymer (see Figure 9, step C) and placed in a medium wherein at least a portion of the polyelectrolyte layers degrade, thereby creating a three-dimensional "tunnel-like" structure that reflects the pattern on the original surface (see Figure 9, step D). It will be appreciated that more complex microstructures could be created based on these simple principles (*e.g.*, by depositing
20 SAMs with different electrostatic character in different regions of a substrate surface and/or by iterative additions of subsequent structures above the deposited non-degradable polymer).

Examples

25 Materials and Methods:

Polymers: The poly(β -amino ester) "Poly 1" (Figure 10) was selected for use in initial experiments based on the relatively slow degradation rate of this polymer at acidic pH ($t_{1/2} > 10$ h at pH = 5.1, 37 °C) (Lynn, D.M., *et al.*, *J. Am. Chem. Soc.*, 122:10761-10768, 2000). As Poly 1 has also been shown to form electrostatic

complexes with polyanions such as DNA in solution, we hypothesized that it would readily absorb to negatively-charged surfaces and model polyanions such as poly(styrene sulfonate) (SPS) and poly(acrylic acid) (PAA) commonly used for LBL assembly.

5 Poly(sodium 4-styrenesulfonate), "SPS", MW ~ 70,000 and highly polymerized calf thymus DNA were obtained from Sigma-Aldrich, St Louis, MO. Linear poly(ethylene imine), "LPEI", MW ~ 25,000, poly(dimethyldiallylammonium chloride) "PDAC", MW ~ 240,000) and poly(acrylic acid), "PAA", MW ~ 90,000 were obtained from Polysciences, Warrington, PA. Poly 1 (see Figure 10, MW ~
10 10,000), was synthesized as described in Lynn *et al.*, *J. Am. Chem. Soc.* 122:10761-10768, 2000, the contents of which are hereby incorporated by reference. All polyelectrolytes were used without further purification or filtration, with the exception of Poly 1. Poly 1 solutions were filtered using a 0.45 μ m membrane syringe filter prior to use. All polymer solutions used for deposition were pH adjusted to 5.1 with a
15 concentration of 5 mM for Poly 1 and 20 mM for all other polyelectrolytes (calculations based on monomer unit). Poly 1 was dissolved in a 100 mM sodium acetate buffer. Other solutions were prepared with deionized water and the pH was adjusted using sodium hydroxide and hydrochloric acid.

20 *Other Chemicals:* The water used for all experimental procedures was obtained from a Milli-Q Reagent Water System (Millipore, Bedford, MA) at 18.2 M Ω cm. For degradation, PBS buffer pH 7.4 (0.1 mM Na₂HPO₄, 150 mM NaCl, 0.027 mM KCl), 100 mM sodium acetate buffer pH 5.1 and TAE buffer pH 8.3 (0.4 mM Tris-acetate and 0.01 mM EDTA) were used. All buffered solutions used for
25 decomposition were salt (NaCl) adjusted to 150 mM to maintain a physiologically relevant salt concentration.

Polyelectrolyte Deposition: Silicon substrates were cut to approximately 1 cm x 2 cm and rinsed with acetone and ethanol. They were then dried using a nitrogen
30 stream and plasma etched to remove any organic materials and to charge the surface

with oxygen radicals. Glass substrates underwent the same procedure. The optical constants (Ns and Ks) for the substrates were then obtained from a Gaertner Variable Angle Ellipsometer (6328 nm, incident angle = 70°). Data were collected and processed using the Gaertner Ellipsometry Measurement Program (GEMP), Version 1.2 software package.

Substrates were then placed in a Carl Zeiss HMS Series Programmable Slide Stainer (Carl Zeiss, Thornwood, NY) where ten precursor bilayers (ca. 100-200 Å) of LPEI/SPS or PDAC/PAA were deposited, terminating with the polyanion monolayer. This was done to assure a strong known net charge on the surface. After measuring the film thickness using ellipsometry, ten bilayers of Poly 1/SPS or Poly 1/PAA were deposited on top of the original film.

The slide stainer was programmed to submerge the substrates in the polycation solution for five minutes and then to rinse the substrates in two successive deionized water baths. The first rinse was of one minute and the following of two minutes and thirty seconds. The substrates were then submerged five more minutes in the polyanion solution and then rinsed in the same manner. After one bilayer was deposited, the substrates were ultra sonicated for four minutes and thirty seconds. This ultra sonication step is believed to improve the surface's topography. The program was then cycled to obtain the desirable bilayers of film.

After deposition, films were dried with nitrogen to remove visible drops of solution from the surface before ellipsometry or profilometry was performed. Multilayers incorporating poly 1 were removed from aqueous water baths immediately after final layers were deposited, dried under a stream of dry nitrogen, placed in a vacuum dessicator and dried overnight to minimize degradation due to incorporated water. Root mean square roughness was determined using a Tencor Corporation KLA Model P10 Surface Profilometer with a 2µm stylus. Reflective FTIR spectra were recorded using a Nicolet Magna-IR 550 Series II Spectrometer. Substrates to be used for reflective FTIR analysis were coated with a thin layer of gold using a thermal evaporator. Decomposition experiments were performed by submerging the substrates in buffered solutions at room temperature or 37°C and

taking measurements by ellipsometry or UV-visible spectroscopy at desired time intervals. The thickness of each sample was determined by ellipsometry at nine different predetermined locations on the substrate surface (measured in triplicate), and the sample was returned to the buffer solution.

5

Results and Discussion:

Growth of Poly 1/SPS and Poly 1/PAA films: The deposition of multi-layer films was followed by ellipsometry as well as profilometry (see Figure 11). Poly 1/SPS films composed of 10 bilayers (on top of the 10 substrate bilayers) were
10 determined to be around 1000 Å thick by profilometry and around 1400 Å thick using ellipsometry. Bilayer growth proved to be directly proportional to film thickness (see Figure 12). Films formed from 10 bilayers of Poly 1/PAA films were thicker than those formed from Poly 1/SPS (around 6000 Å). These results are consistent with previous studies showing a relationship between film thickness and pH for weak
15 polyacid systems (Shiratori, S.S., *et al.*, *Macromolecules*, **33**:4213-4219, 2000). The films formed from both polymer systems were extremely smooth considering their thickness; the root mean square roughness (RMS) for both systems obtained by profilometry ranged from 16.9 Å to 60.2 Å.

To verify that Poly 1 was being incorporated in the films, Poly 1/SPS films
20 were grown on gold substrates for analysis by reflective FTIR. The observation of a strong peak between 1725 and 1750 cm⁻¹ corresponding to the carboxyl stretch of Poly 1 confirms the presence of Poly 1 in the films (see Figure 13). The Poly 1/SPS system was selected for the FTIR, rather than the Poly 1/PAA systems, to prevent the carboxyl group of the PAA from obscuring the CO stretch in Poly 1.

25

Decomposition of Poly 1/SPS and Poly 1/PAA films: Once procedures for the construction of films using Poly 1 were optimized, experiments to investigate film decomposition were performed. Films were incubated at pH 5.1, 7.4 and 8.3 in order to examine decomposition at pH and temperature values likely to be encountered in
30 controlled release applications. Poly 1/SPS films decomposed over a 40-hour period

in PBS pH 7.4 at 37 °C (see Figure 14). Interestingly, decomposition appeared to occur by surface erosion and films remained smooth and consistent throughout the decomposition process, allowing decomposition to be monitored conveniently by ellipsometry. In general, the rate of decomposition increased with increasing pH.

5 Poly 1/SPS films placed in TAE buffer at pH 8.3 decomposed in under nine hours (see Figure 15) and more slowly under acidic conditions. These pH/rate data are consistent with a hydrolytic mechanism of degradation and erosion, similar to that previously observed for polymer 1 in solution (Lynn, D.M., 2000). Poly 1 is insoluble in aqueous media at pH 7.4, suggesting that degradation or erosion is occurring via

10 hydrolysis rather than decomplexation and dissociation of layers of Poly 1 at higher pH.

Film erosion rates were also dependent on the structures of the incorporated polyanions. For example, while 100 nm thick Poly 1/SPS films eroded completely over a period of 40 hours at pH 7.4 (Figure 2), 600 nm films formed from Poly 1 and

15 PAA degraded completely over a period of 9 hours under identical conditions. This behavior is consistent with the pH/dissolution profile observed for other weak polyacid multilayer systems, in which the increased ionization of PAA at elevated pH contributes to repulsive electrostatic interactions (Sukhishvili, S.A., *et al.*, *S. Macromolecules*, **35**:301-310, 2002; Sukhishvili, S.A., *et al.*, *J. Am. Chem. Soc.*, **122**:9550-9551, 2000). Additionally, films containing thick layers of PAA often

20 possess a lower overall effective crosslink density than more compact films constructed from strong polyelectrolytes such as SPS (Shiratori, S.S., 2000; Lvov, Y., *et al.*, *Langmuir*, **9**:481-486, 1993); the less crosslinked morphology may support more rapid permeation of water and breakdown of the polymer layers.

25 The ellipsometric data in Figure 2 suggest that film erosion occurs gradually, rather than by the bulk deconstruction observed for weak polyacid or salt-deconstructed systems (Sukhishvili, S.A., 2002; Sukhishvili, S.A., 2000; For general examples of salt-induced "deconstruction" of polyelectrolyte multilayers, see: Dubas, S.T.; Schlenoff, J.B., *Macromolecules*, **34**:3736-3740, 2001; Schuler, C., *et al.*,

30 *Biomacromolecules*, **2**:921-926, 2001). Preliminary AFM analysis of partially eroded

films is also consistent with this gradual erosion process – surface roughness values for partially eroded films (RMS roughness – 6.9 nm) were less than the thickness of an average bilayer (10 nm) and surfaces were consistent over 1 μm (Hammond, P.T., 1998) portions of the film. We continue to investigate the factors governing erosion at various length scales and spatial resolutions, as the ability to control erosion in a “top-down” manner could introduce significant advantages from a release standpoint and allow precise control over the sequences by which one or more incorporated components are released. The different decomposition rates provide a potential means for controlling the exact decomposition rates of films by customization with these two or any other polyanions.

Controlled release of DNA from Poly 1/DNA films: Preliminary experiments designed to explore the application of these decomposable thin films to the controlled release of polyanions were done by adsorbing polyanionic dyes and calf thymus DNA into the decomposable polymeric films. Adsorption of DNA by electrostatic layer-by-layer deposition was achieved by the negative charge of the phosphate-sugar group that composes the helix. Poly 1/DNA films were deposited on silicon substrates previously prepared with ten precursor bilayers of LPEI/SPS. These films were measured by ellipsometry and film thickness ranged from 800 Å to 1000 Å (see Figure 16). Poly 1/DNA films decomposed over a 50-hour period in PBS buffer pH 7.4 at 37 °C (see Figure 17).


Other embodiments

Those of ordinary skill in the art will appreciate that the foregoing has been a description of certain preferred embodiments of the present invention. This description is not intended to limit the spirit or scope of the present invention, as embodied in the following claims.

Claims

What is claimed is:

1. A decomposable thin film comprising a plurality of polyelectrolyte layers of alternating charge, wherein decomposition of the thin film is characterized by degradation of at least a portion of the polyelectrolyte layers.
2. The decomposable thin film of claim 1, wherein:
the thin film comprises alternating polycationic and polyanionic layers,
and
decomposition of the thin film is characterized by hydrolytic degradation of a member of the polycationic layers, the polyanionic layers, and both.
3. The decomposable thin film of claim 1, wherein a portion of the polyelectrolyte layers comprises a member of a synthetic polyelectrolyte, a natural polyelectrolyte, and both.
4. The decomposable thin film of claim 1, wherein at least a portion of the polyelectrolyte layers comprises a polymer selected from polyesters, polyanhydrides, polyorthoesters, polyphosphazenes, polyphosphoesters, and any combination thereof.
5. The decomposable thin film of claim 4; wherein the polyesters are selected from poly(β -amino ester)s, poly(L-lactide-co-L-lysine), poly(serine ester), poly(4-hydroxy-L-proline ester), poly[α -(4-aminobutyl)-L-glycolic acid], and any combination thereof.
6. The decomposable thin film of claim 5, wherein the poly(β -amino ester) is selected from




wherein:

3 linker A and linker B are each independently selected from the group
 4 consisting of carbon chains of 1 to 30 carbon atoms, heteroatom-containing
 5 carbon chains of 1 to 30 atoms, and carbon chains and heteroatom-containing
 6 carbon chains with at least one substituent selected from the group consisting
 7 of branched and unbranched alkyl, branched and unbranched alkenyl,
 8 branched and unbranched alkynyl, amino, alkylamino, dialkylamino,
 9 trialkylamino, aryl, ureido, heterocyclic, aromatic heterocyclic, cyclic,
 10 aromatic cyclic, halogen, hydroxyl, alkoxy, cyano, amide, carbamoyl,
 11 carboxylic acid, ester, carbonyl, carbonyldioxy, alkylthioether, and thiol
 12 groups;

13 R₁ and R₂ are each independently selected from the group consisting
 14 of hydrogen, branched and unbranched alkyl, branched and unbranched
 15 alkenyl, branched and unbranched alkynyl, aryl, halogen, hydroxyl, alkoxy,
 16 carbamoyl, carboxyl ester, carbonyldioxy, amide, thiohydroxyl,
 17 alkylthioether, amino, alkylamino, dialkylamino, trialkylamino, cyano, ureido,
 18 a substituted alkanoyl group, cyclic, cyclic aromatic, heterocyclic, and
 19 aromatic heterocyclic groups, each of which may be substituted with at least
 20 one substituent selected from the group consisting of branched and
 21 unbranched alkyl, branched and unbranched alkenyl, branched and
 22 unbranched alkynyl, amino, alkylamino, dialkylamino, trialkylamino, aryl,
 23 ureido, heterocyclic, aromatic heterocyclic, cyclic, aromatic cyclic, halogen,

hydroxyl, alkoxy, cyano, amide, carbamoyl, carboxylic acid, ester, carbonyl, carbonyldioxyl, alkylthioether, and thiol groups; and
n is an integer between 5 and 10,000.

7. The decomposable thin film of claim 5, wherein the poly(β -amino ester) is



8. The decomposable thin film of claim 4, wherein at least a portion of the polymer comprises a member of an anionic group, a cationic group, and any combination thereof.

9. The decomposable thin film of claim 8, wherein the member is incorporated in the backbone of the polymer, covalently attached to the backbone of the polymer, or covalently attached to a pendant group of the polymer.

10. The decomposable thin film of claim 8, wherein the member comprises a carboxylate, sulfonate, sulphate, phosphate, nitrate, protonated amine, quaternary ammonium, or phosphonium group.

11. The decomposable thin film of claim 1, wherein at least a portion of the polyelectrolyte layers comprises a polymer selected from poly(styrene sulfonate), poly(acrylic acid), linear poly(ethylene imine), poly(diallyl dimethyl ammonium chloride), poly(allylamine hydrochloride), and any combination thereof.

12. The decomposable thin film of claim 1, wherein the degradation is characterized by at least one of hydrolytic, thermal, enzymatic, and photolytic.

- 1 13. The decomposable thin film of claim 1, wherein at least a portion of the
2 polyelectrolyte layers comprises a biodegradable polymer.
3
- 4 14. The decomposable thin film of claim 13, wherein the biodegradable polymer
5 is selected from polyhydroxyacids, polypropylfumerates, polycaprolactones,
6 polyamides, poly(amino acids), polyacetals, polyethers, biodegradable
7 polycyanoacrylates, biodegradable polyurethanes, polysaccharides, and co-
8 polymers, mixtures, and adducts thereof.
9
- 10 15. The decomposable thin film of claim 1, wherein at least a portion of the
11 polyelectrolyte layers comprises a thermally degradable polymer.
12
- 13 16. The decomposable thin film of claim 1, wherein at least a portion of the
14 polyelectrolyte layers comprises a photolytically degradable polymer.
15
- 16 17. The decomposable thin film of claim 1, wherein at least a portion of the
17 polyelectrolyte layers comprises an electroactive polymer.
18
- 19 18. The decomposable thin film of claim 1, wherein at least a portion of the
20 polyelectrolyte layers comprises a zwitterionic polymer.
21
- 22 19. The decomposable thin film of claim 18, wherein at least a portion of the
23 polyelectrolyte layers comprises alternating layers of a first zwitterionic
24 polymer and a second zwitterionic polymer, wherein the first polymer is a
25 polycation and the second polymer is a polyanion at a selected non-
26 physiological pH and the first polymer is a polyanion and the second polymer
27 is a polycation at a physiological pH.
28
- 29 20. The decomposable thin film of claim 1, wherein at least a portion of the
30 polyelectrolyte layers comprises a mixture of degradable and non-degradable

1 polyelectrolytes.

2

3 21. The decomposable thin film of claim 1, wherein the degradation rate of the
4 layers varies such that the decomposition rate of the thin film is not a constant.

5

6 22. The decomposable thin film of claim 1, further comprising a layer of cells
7 deposited on the surface of the thin film.

8

9 23. The decomposable thin film of claim 22, wherein the cells are selected from
10 connective tissue cells, organ cells, muscle cells, nerve cells, stem cells, cancer
11 cells, and any combination thereof.

12

13 24. The decomposable thin film of claim 1, wherein at least a portion of the layers
14 comprise an entity selected from a biomolecule, a small molecule, a bioactive
15 agent, and any combination thereof.

16

17 25. The decomposable thin film of claim 24, wherein a second portion of the
18 layers comprise a second entity selected from a biomolecule, a small
19 molecule, a bioactive agent, and any combination thereof.

20

21 26. The decomposable thin film of claim 24, wherein the concentration of the
22 entity in the thin film varies with depth.

23

24 27. The decomposable thin film of claim 24, wherein the small molecule is a drug.

25

26 28. The decomposable thin film of claim 24, wherein the entity is associated with
27 a polyelectrolyte in a layer of the thin film.

28

29 29. The decomposable thin film of claim 28, wherein the entity is associated via
30 an interaction selected from covalent bond, a hydrogen bond, an electrostatic

- 1 interaction, a van der Waals interaction, a hydrophobic interaction, a magnetic
2 interaction and any combination of the above.
3
- 4 30. The decomposable thin film of claim 24, wherein the entity is mixed with a
5 polyelectrolyte in a layer of the thin film.
6
- 7 31. The decomposable thin film of claim 1, further comprising a member of a cell
8 adhesion sequence, a targeting sequence, and both disposed in a top layer of
9 the thin film.
10
- 11 32. The decomposable thin film of claim 1, wherein the thin film is deposited on a
12 non-planar substrate.
13
- 14 33. The decomposable thin film of claim 32, wherein the thin film is deposited on
15 a substrate having a shape selected from particles, tube, sphere, strand, coiled
16 strand, and capillary network.
17
- 18 34. The decomposable thin film of claim 32, wherein degradation of the thin film
19 enables dissolution of the substrate material.
20
- 21 35. The decomposable thin film of claim 1, wherein the thin film is adapted and
22 constructed as a hollow shell.
23
- 24 36. The decomposable thin film of claim 32, wherein the substrate material
25 diffuses through the thin film when the thin film-substrate combination is
26 placed in a pre-selected medium.
27
- 28 37. The decomposable thin film of claim 32, wherein the substrate comprises a
29 drug.
30

- 1 38. The decomposable thin film of claim 1, wherein the thin film is disposed on a
2 substrate, wherein the surface properties of the substrate vary across a surface
3 of the substrate.
4
- 5 39. The decomposable thin film of claim 1, wherein the thin film is disposed on a
6 substrate comprising a material selected from metals, metal oxides, plastics,
7 ceramics, silicon, glasses, mica, graphite, hydrogels, polymers, and any
8 combination thereof.
9
- 10 40. The decomposable thin film of claim 39, wherein a primer layer is interposed
11 between the thin film and the substrate, wherein the primer layer comprises a
12 polyelectrolyte bilayer.
13
- 14 41. The decomposable thin film of claim 40, wherein the polyelectrolyte bilayer
15 comprises a polymer selected from poly(styrene sulfonate) and poly(acrylic
16 acid) and a polymer selected from linear poly(ethylene imine), poly(diallyl
17 dimethyl ammonium chloride), and poly(allylamine hydrochloride).
18
- 19 42. A method of releasing an entity from a thin film comprising:
20 associating the entity with a thin film comprising a plurality of
21 polyelectrolyte layers of alternating charge; and
22 placing the thin film in a medium in which at least a portion of the thin
23 film decomposes via the substantially sequential degradation of at least a
24 portion of the polyelectrolyte layers.
25
- 26 43. The method of claim 42, wherein the degradation is at least partially
27 hydrolytic.
28
- 29 44. The method of claim 42, wherein the degradation is at least partially
30 enzymatic.

- 1
2 45. The method of claim 42, wherein the degradation is at least partially thermal.
3
4 46. The method of claim 42, wherein the degradation is at least partially
5 photolytic.
6
7 47. The method of claim 42, wherein the degradation rate is not constant.
8
9 48. The method of claim 42, further comprising depositing alternating polyanionic
10 and polycationic layers on a substrate, wherein the step of associating
11 comprises associating the entity with at least a portion of a member of the
12 polycationic and polyanionic layers.
13
14 49. The method of claim 42, wherein the entity to be released is a member of a
15 component of the polycationic layers, a component of the polyanionic layers,
16 and both.
17
18 50. The method of claim 42, further comprising depositing the thin film on a
19 substrate.
20
21 51. The method of claim 50, wherein the substrate has a shape selected from non-
22 planar, particles, tube, sphere, strand, coiled strand, and capillary network.
23
24 52. The method of claim 50, further comprising allowing the substrate material to
25 diffuse through the thin film.
26
27 53. The method of claim 50, further comprising dissolving the substrate.
28
29 54. The method of claim 42, further comprising preparing a substrate, and
30 depositing the plurality of polyelectrolyte layers on the substrate.


- 1
- 2 55. The method of claim 54, wherein the step of preparing the substrate comprises
- 3 a member of charging the surface of the substrate, depositing a primer layer on
- 4 the substrate, and any combination thereof.
- 5
- 6 56. The method of claim 55, wherein the step of charging the surface of the
- 7 substrate comprises a member of depositing a self-assembled monolayer on
- 8 the substrate surface, depositing a uniform coating of a polymer on the
- 9 substrate surface and patterning the uniform coating by photolithography,
- 10 selectively exposing the substrate surface to plasmas, selectively exposing the
- 11 substrate surface to electromagnetic radiation, selectively exposing the
- 12 substrate surface to electron beams, and any combination thereof.
- 13
- 14 57. The method of claim 55, wherein the step of depositing a primer layer
- 15 comprises at least one polyelectrolyte bilayer.
- 16
- 17 58. The method of claim 57, wherein the polyelectrolyte bilayer comprises a
- 18 polymer selected from poly(styrene sulfonate) and poly(acrylic acid) and a
- 19 polymer selected from linear poly(ethylene imine), poly(diallyl dimethyl
- 20 ammonium chloride), and poly(allylamine hydrochloride).
- 21
- 22 59. The method of claim 42, further comprising disposing a member of a cell
- 23 adhesion sequence, a targeting sequence, and both in a top layer of the thin
- 24 film.
- 25
- 26 60. The method of claim 42, wherein the entity is a plurality of cells deposited on
- 27 a surface of the thin film.
- 28
- 29 61. The method of claim 42, further comprising associating a second entity with
- 30 the thin film.

62. The method of claim 42, wherein the entity is not released at a constant rate.

63. The method of claim 42, wherein at least a portion of the polyelectrolyte layers comprises a polymer selected from polyesters, polyanhydrides, polyorthoesters, polyphosphazenes, polyphosphoesters, and any combination thereof.

64. The method of claim 63, wherein the polyesters are selected from poly(β -amino ester)s, poly(L-lactide-co-L-lysine), poly(serine ester), poly(4-hydroxy-L-proline ester), poly(α -(4-aminobutyl)-L-glycolic acid], and any combination thereof.

65. The decomposable thin film of claim 64, wherein the poly(β -amino ester) is selected from



wherein:


linker A and linker B are each independently selected from the group consisting of carbon chains of 1 to 30 carbon atoms, heteroatom-containing carbon chains of 1 to 30 atoms, and carbon chains and heteroatom-containing carbon chains with at least one substituent selected from the group consisting of branched and unbranched alkyl, branched and unbranched alkenyl, branched and unbranched alkynyl, amino, alkylamino, dialkylamino, trialkylamino, aryl, ureido, heterocyclic, aromatic heterocyclic, cyclic,

1 aromatic cyclic, halogen, hydroxyl, alkoxy, cyano, amide, carbamoyl,
 2 carboxylic acid, ester, carbonyl, carbonyldioxyl, alkylthioether, and thiol
 3 groups;

4 R_1 and R_2 are each independently selected from the group consisting
 5 of hydrogen, branched and unbranched alkyl, branched and unbranched
 6 alkenyl, branched and unbranched alkynyl, aryl, halogen, hydroxyl, alkoxy,
 7 carbamoyl, carboxyl ester, carbonyldioxyl, amide, thiohydroxyl,
 8 alkylthioether, amino, alkylamino, dialkylamino, trialkylamino, cyano, ureido,
 9 a substituted alkanoyl group, cyclic, cyclic aromatic, heterocyclic, and
 10 aromatic heterocyclic groups, each of which may be substituted with at least
 11 one substituent selected from the group consisting of branched and
 12 unbranched alkyl, branched and unbranched alkenyl, branched and
 13 unbranched alkynyl, amino, alkylamino, dialkylamino, trialkylamino, aryl,
 14 ureido, heterocyclic, aromatic heterocyclic, cyclic, aromatic cyclic, halogen,
 15 hydroxyl, alkoxy, cyano, amide, carbamoyl, carboxylic acid, ester, carbonyl,
 16 carbonyldioxyl, alkylthioether, and thiol groups; and

17 n is an integer between 5 and 10,000.

18
 19 66. The decomposable thin film of claim 64, wherein the poly(β -amino ester) is



20

21

22 67. The method of claim 63, wherein at least a portion of the polymer comprises a
 23 member of an anionic group, a cationic group, and any combination thereof.

24

25 68. The method of claim 67, wherein the member is incorporated in the backbone
 26 of the polymer, covalently attached to the backbone of the polymer, or

- 1 covalently attached to a pendant group of the polymer.
2
- 3 69. The method of claim 67, wherein the member comprises a carboxylate,
4 sulfonate, sulphate, phosphate, nitrate, protonated amine, quaternary
5 ammonium, or phosphonium group.
6
- 7 70. The method of claim 42, wherein at least a portion of the polyelectrolyte
8 layers comprises a member of the group consisting of poly(styrene sulfonate),
9 poly(acrylic acid), linear poly(ethylene imine), poly(diallyl dimethyl
10 ammonium chloride), poly(allylamine hydrochloride), and any combination
11 thereof.
12
- 13 71. The method of claim 42, wherein at least a portion of the polyelectrolyte
14 layers comprises a biodegradable polymer.
15
- 16 72. The method of claim 71, wherein the biodegradable polymer is selected from
17 polyhydroxyacids, polypropylfumerates, polycaprolactones, polyamides,
18 poly(amino acids), polyacetals, polyethers, biodegradable polycyanoacrylates,
19 biodegradable polyurethanes, polysaccharides, and co-polymers, mixtures, and
20 adducts thereof.
21
- 22 73. The method of claim 42, wherein at least a portion of the polyelectrolyte
23 layers comprises a non-biodegradable biocompatible polymer.
24
- 25 74. The method of claim 73, wherein the non-biodegradable biocompatible
26 polymer is selected from polystyrenes, polyesters, non-biodegradable
27 polyurethanes, polyureas, poly(ethylene vinyl acetate), polypropylene,
28 polymethacrylate, polyethylene, polycarbonates, poly(ethylene oxide)s, and
29 co-polymers, mixtures, and adducts thereof.
30

- 1 75. The method of claim 74, wherein the non-biodegradable biocompatible
2 polymer comprises a charged group incorporated in the backbone of the
3 polymer, covalently attached to the backbone of the polymer, or covalently
4 attached to a pendant group of the polymer.
5
- 6 76. The method of claim 42, wherein at least a portion of the polyelectrolyte
7 layers comprises a thermally degradable polymer.
8
- 9 77. The method of claim 42, wherein at least a portion of the polyelectrolyte
10 layers comprises a photolytically degradable polymer.
11
- 12 78. The method of claim 42, wherein at least a portion of the polyelectrolyte
13 layers comprises an electroactive polymer.
14
- 15 79. The method of claim 42, wherein at least a portion of the polyelectrolyte
16 layers comprises a zwitterionic polymer.
17
- 18 80. The method of claim 79, wherein at least a portion of the polyelectrolyte
19 layers comprises alternating layers of a first zwitterionic polymer and a second
20 zwitterionic polymer, wherein the first polymer is a polycation and the second
21 polymer is a polyanion at a selected non-physiological pH and the first
22 polymer is a polyanion and the second polymer is a polycation at a
23 physiological pH.
24
- 25 81. The method of claim 42, wherein at least a portion of the polyelectrolyte
26 layers comprises a mixture of degradable and non-degradable polyelectrolytes.
27
- 28 82. The method of claim 42, wherein at least a portion of the layers comprise a
29 moiety selected from a biomolecule, a small molecule, a bioactive agent, and
30 any combination thereof.

- 1
- 2 83. The method of claim 82, wherein the concentration of the moiety in the thin
3 film varies with depth.
4
- 5 84. The method of claim 82, wherein the small molecule is a drug.
6
- 7 85. The method of claim 82, wherein the moiety is associated with a
8 polyelectrolyte in a layer of the thin film.
9
- 10 86. The method of claim 82, wherein the moiety is mixed with a polyelectrolyte in
11 a layer of the thin film.
12
- 13 87. The method of claim 85, wherein associating comprises linking the entity to a
14 polyelectrolyte material through a member of a covalent bond, a hydrogen
15 bond, an electrostatic interaction, a van der Waals interaction, a hydrophobic
16 interaction, a magnetic interaction and any combination of the above.
17
- 18 88. The method of claim 42, wherein the method further comprises depositing the
19 plurality of polyelectrolyte layers on a substrate.
20
- 21 89. The method of claim 42, further comprising depositing the thin film on a
22 substrate via layer-by-layer deposition.
23
- 24 90. The method of claim 89, wherein the step of associating comprises, after a
25 predetermined layer is deposited, associating the entity with the layer.
26
- 27 91. The method of claim 89, wherein the layers are deposited by a member of dip
28 coating, spray coating, brush coating, roll coating, spin casting, and any
29 combination thereof.
30

- 1 92. The method of claim 42, further comprising placing the thin film in a second
2 medium in which a second portion of the thin film decomposes.
3
- 4 93. The method of claim 42, wherein the medium is characterized by a member of
5 endosomal conditions and physiological conditions.
6
- 7 94. A method of generating a three dimensional microstructure on a substrate
8 surface, comprising steps of:
9 creating a charged region on the substrate surface;
10 depositing a plurality of polyelectrolyte layers of alternating charge on
11 the charged region;
12 depositing a first non-degradable material over the substrate and the
13 plurality of polyelectrolyte layers; and
14 placing the coated substrate in a medium in which at least a portion of
15 the polyelectrolyte layers degrade.
16
- 17 95. The method of claim 94, wherein the degradation is characterized by a
18 member of hydrolytic, enzymatic, thermal, photolytic, and any combination of
19 the above.
20
- 21 96. The method of claim 94, wherein the step of creating a charged region
22 comprises depositing a self-assembled monolayer.
23
- 24 97. The method of claim 94, wherein the step of creating a charged region
25 comprises depositing a uniform coating of a polymer on the substrate surface
26 and patterning the uniform coating by photolithography.
27
- 28 98. The method of claim 94, wherein the step of creating a charged region
29 comprises selectively exposing the substrate surface to a member from the
30 group consisting of plasmas, electromagnetic radiation, electron beams, and

1 any combination thereof.

2

3 99. The method of claim 94, further comprising, following the step of depositing a
4 non-degradable material,

5 creating a charged region on the first non-degradable material;

6 depositing a plurality of polyelectrolyte layers of alternating charge on
7 the charged region; and

8 depositing a second non-degradable material over the first non-
9 degradable material and the plurality of layers.

10

11 100. The method of claim 99, wherein the step of creating a charged region on the
12 first non-degradable material comprises depositing a self-assembled
13 monolayer.

14

15 101. The method of claim 99, wherein the second non-degradable material is the
16 same as the first non-degradable material.

17

18 102. The method of claim 94, wherein a surface composition of a first portion of
19 the substrate is not the same as the surface composition of a second portion of
20 the substrate.

21





Figure 1 (Prior Art)

**Figure 2**




Figure 3






Figure 4

FIGURE 5

FIGURE 6




Figure 7




Figure 8





FIGURE 9



Poly 1

Figure 10




Figure 11




Figure 12




Figure 13




Figure 14




Figure 15




Figure 16




Figure 17

INTERNATIONAL SEARCH REPORT

In tional Application No
PCT/US 02/34191

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08G63/685 C30B33/00 A61K9/50 B01J13/02 B01J13/22
C08B37/00 C08G75/02 C08G75/20 C08J5/22 C08G59/42
C08G77/00 C09D5/44 C09D167/06 H01B13/06 H01B13/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08G C30B A61K B01J C08B B01D C08J C09D H01B C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	WO 01 94441 A (KAMM BIRGIT ; KRAUSE THOMAS (DE); ALLWOHN JUERGEN (DE); BIRKEL SUSA) 13 December 2001 (2001-12-13) page 2, line 4 -page 4, line 24 page 10, line 30 -page 11, line 18 abstract; claims 1-28; examples 1-4	1-102
X	WO 00 77281 A (TRAU DIETER ; RENNEBERG REINHARD (CN); MAX PLANCK GESELLSCHAFT (DE)) 21 December 2000 (2000-12-21) page 4, line 27 -page 6, line 4 page 7, line 7 -page 8, line 20 page 11, line 5 -page 12, line 13 page 15, line 13 - line 18 abstract; claims 1-31 --- -/--	1-102



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

9 January 2003

Date of mailing of the international search report

17/01/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

G1omm, B

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/34191

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F283/01 C08G63/695 C08F2/46 H01B13/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 99 47253 A (MAX PLANCK GESELLSCHAFT ;CARUSO FRANK (DE); DONATH EDWIN (DE); CAR) 23 September 1999 (1999-09-23) page 4, line 19 -page 5, line 9 page 7, line 16 -page 8, line 17 abstract; claims 1-26; examples 1-5 ---	1-102
X	DE 198 12 083 A (MAX PLANCK GESELLSCHAFT) 30 September 1999 (1999-09-30) column 2, line 24 -column 3, line 45 abstract; claims 1-36; examples 1-10 ---	1-102
Y	WO 96 03147 A (PAPARELLA ANNAMARIA ;BENEDETTI LUCA (IT); FIDIA ADVANCED BIOPOLYME) 8 February 1996 (1996-02-08) page 2, line 17 -page 3, line 7 page 4, line 6 -page 5, line 13 abstract; claims 1-15; examples 1-8 --- -/--	1-102

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

9 January 2003

Date of mailing of the international search report

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

G1omm, B

INTERNATIONAL SEARCH REPORT

Int'l Application No
PCT/US 02/34191

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4 191 811 A (HODGDON RUSSELL B) 4 March 1980 (1980-03-04) column 2, line 24 - line 68 abstract; claims 1-8; examples 1-10 ---	1-102
Y	GB 1 213 803 A (FORD MOTOR COMPANY LTD.) 25 November 1970 (1970-11-25) page 1, line 23 -page 2, line 24 abstract; claims 1-38; examples 1-10 ---	1-102
Y	GB 1 213 805 A (FORD MOTOR COMPANY LTD.) 25 November 1970 (1970-11-25) page 1, line 22 -page 2, line 47 abstract; claims 1-17; examples 1-6 -----	1-102

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US.02/34191

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0194441	A	13-12-2001	DE 10027393 A1	13-12-2001
			AU 6228101 A	17-12-2001
			WO 0194441 A1	13-12-2001
WO 0077281	A	21-12-2000	AT 226267 T	15-11-2002
			DE 60000622 D1	21-11-2002
			WO 0077281 A1	21-12-2000
			EP 1190123 A1	27-03-2002
WO 9947253	A	23-09-1999	DE 19812083 A1	30-09-1999
			EP 0972563 A1	19-01-2000
			AT 228883 T	15-12-2002
			WO 9947253 A1	23-09-1999
			WO 9947252 A2	23-09-1999
			EP 1064087 A2	03-01-2001
			EP 1064088 A1	03-01-2001
			JP 2002506719 T	05-03-2002
			US 6479146 B1	12-11-2002
			WO 0003797 A1	27-01-2000
			EP 1098696 A1	16-05-2001
			JP 2002520151 T	09-07-2002
DE 19812083	A	30-09-1999	DE 19812083 A1	30-09-1999
			AT 228883 T	15-12-2002
			WO 9947253 A1	23-09-1999
			WO 9947252 A2	23-09-1999
			EP 1064087 A2	03-01-2001
			EP 1064088 A1	03-01-2001
			JP 2002506719 T	05-03-2002
			US 6479146 B1	12-11-2002
WO 9603147	A	08-02-1996	IT PD940139 A1	26-01-1996
			AU 2818795 A	22-02-1996
			WO 9603147 A1	08-02-1996
US 4191811	A	04-03-1980	US 4110265 A	29-08-1978
GB 1213803	A	25-11-1970	AT 301720 B	11-09-1972
			BE 704587 A	15-02-1968
			DE 1621911 A1	20-08-1970
			ES 345361 A1	01-05-1969
			FI 51055 B	30-06-1976
			FR 1538217 A	30-08-1968
			GB 1213805 A	25-11-1970
			GB 1213806 A	25-11-1970
			JP 48039218 B	22-11-1973
			NL 6713440 A	04-04-1968
			NO 127017 B	24-04-1973
			NO 125853 B	13-11-1972
			SE 338911 B	20-09-1971
			US 3501390 A	17-03-1970
			US 3630883 A	28-12-1971
			AT 297180 B	10-03-1972
			BE 704586 A	15-02-1968
			DE 1720717 A1	10-02-1972
			ES 345360 A1	16-05-1969
			FI 45861 B	30-06-1972
			FR 1544227 A	31-10-1968

Form PCT/ISA/210 (patent family annex) (July 1992)

Information on patent family members

PCT/US 02/34191

Form PCT/ISA/210 (patent family annex) (July 1992)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☒ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.